

Nunchuck's fluidic path chemical compatibility

Introduction

This tech note provides information on the composition and chemical compatibility of the Nunchuck fluidic path materials including Nun, dispensing needles, tubing, and collection vials. **Table 1** lists the materials in Nunchuck's fluidic path. This compatibility is important in considering the potential use of the Nunchuck in several applications, including lipid nanoparticles, nanoparticles, liposomes, micelles, and nanoemulsions. The compatibility of the microfluidic chip is based on the effect a chemical may have on the swelling and dissolution of the PDMS-bonded glass. Please refer to **Table 2** for the reagents compatible with Nunchuck consumables.

In general, solvents with low solubility ($\delta \geq 9.9$ cal^{1/2} cm^{-3/2}) and moderate to high polar ($\mu > 1.4$ D) contributions are compatible with the Nun. Stainless steel and polypropylene are generally high in chemical resistance but should not be used in contact with halogenated and aromatic hydrocarbons or strong oxidizing acids.

On the other hand, high-solubility solvents which tend to be nonpolar or only slightly polar ($\mu \leq 1$ D)



Figure 1: Nunchuck is the one-and-done LNP maker.

are incompatible with the Nun. PDMS will absorb these solvents from a microchannel, and get saturated with the solvent over time. **Table 3** shows the reagents which are not compatible with the Nunchuck consumables. We do not support the use of these chemicals on the Nunchuck. Be advised that this is not an exhaustive list and if you would like to use chemicals that are not explicitly listed in **Table 2**, contact Unchained Labs before proceeding.

Consumable Component	Material Composition
Dispensing needles	304 Stainless Steel and Polypropylene Plastic
Teflon tubing	PTFE
Chip	PDMS bonded to Soda Lime Glass

Table 1: Consumable materials used in Nunchuck.

Chemical	Maximum Concentration/Composition
Acidic /Aqueous (pH<7)	8% Acetic acid (vinegar) 10% Nitric Acid
Basic/Aqueous (PH>7)	20% Ammonium hydroxide 10% Potassium Hydroxide
Organic Solvents - Alcohols - Nitrils - Disubstituted amides - Tetrasubstituted ureas - Sulfoxides - Sulfone - Pyridines - Nitro compounds	- Propanol, ethanol, methanol, glycerol - Acetonitrile - NMP, dimethylformamide (DMF) 1, 1, 3, 3-tetramethylurea - Dimethyl Sulfoxide (DMSO) - Tetramethylene sulfone - Pyridines - Nitromethane

Table 2: Lists of chemically compatible compounds with Nunchuck's consumables materials.

Chemical	Concentration/Composition
Acidic /Aqueous (pH<7)	- Phosphoric acid - Sulfuric acid
Basic/Aqueous (PH>7)	Sodium hydroxide
Organic Solvents - Acyclic and cyclic hydrocarbons - Aromatic hydrocarbons - Halogenated compounds - Ethers	- Pentanes, hexanes, heptane, cyclohexane - Xylenes, toluene, benzene - Chloroform, trichloroethylene - Diethyl ether, dimethoxyethane, tetrahydrofuran

Table 3: Lists of chemically non-compatible compounds with Nunchuck's consumables materials.



Unchained Labs
 6870 Koll Center Parkway
 Pleasanton, CA 94566
 Phone: 1.925.587.9800
 Toll-free: 1.800.815.6384
 Email: info@unchainedlabs.com

© 2022 Unchained Labs. All rights reserved. The Unchained Labs logo, Nunchuck the Nunchuck logo are trademarks and/or registered trademarks of Unchained Labs. All other brands or product names mentioned are trademarks owned by their respective organizations.